

CHAMOTTE MORTARS

Class	Content of Al ₂ O ₃ +TiO ₂ %	Refractoriness °C	Humidity content %	Residue on sieve 0,5 mm %
FM 36	36	1730	5	< 5
FM 30	30	1710	5	< 5



Chamotte mortars are supplied in bags of 20 kg.

CHAMOTTE FRACTIONS

Class	Content of Al ₂ O ₃ +TiO ₂ %	Refractoriness °C	Humidity content %
FF 36	36	1730	3
FF 30	30	1710	3



Chamotte fractions are produced according to clients' requirements.

These are supplied in bulk or in containers "Big Bag".

The company offers its clients fractions with different granulometric content.